



## NACAR RED

Quality high activity coconut based granular activated carbon chemically impregnated for chemisorption of mercury.

### Features

- High activity
- Low attrition
- Low dust

### Benefits

- Accommodates both physical & chemical sorption
- Minimal carbon fines
- Easy handling and improved safety

### Physico-chemical specifications

Apparent density (g/cc)	(ASTM D2854)	0.44-0.55
Moisture as packed (% max)	(ASTM D2867)	5
CCl <sub>4</sub> adsorption (% min) - Base Carbon	(ASTM D5742)	60
Hardness No., ball pan test (min) - Base Carbon	(ASTM D3802)	92

### Properties

Typical loading of Hg (% W/W)	3-5%
-------------------------------	------

### Available particle sizes (ASTM D2862)

ASTM mesh size	On larger screen (% max)	Between screen sizes (% min)	Through smaller screen (% max)
4x8	5	90	5
6x12	5	90	5

This product can be tailored according to specific requests.

### Packaging

NACAR RED is supplied in 15 and 67 gallon fiberboard drums. Other packaging is available upon request.

Ed. 05/05- Revision No. 3.0  
 PICA USA, INC., 432 McCormick Blvd., Columbus, OH 43213  
 Tel: 614-864-8100 • Fax: 614-864-9914 • Toll free number: 1-888-GO-4-PICA.  
 PICA USA, INC. reserves the right to modify these specifications without prior notice.

